

DuPont 5874

SILVER/SILVER CHLORIDE COMPOSITION FOR SCREEN PRINTING

Technical Data Sheet

Product Description

DuPont 5874 is solvent-based composition designed for screen-printing on polyester. The composition is suitable for use as a reference/counter electrode for electrochemical sensors, for iontophoretic anodes and cathodes, or for a wide variety of biomedical applications.

Product Benefits

- Low electrode polarization
- High Stability reference potential
- High solids for printing thick electrodes
- Fast drying
- Equal electrode capacity for iontophoretic anode & cathode.

Processing

Printing

DuPont 5874 should be mixed thoroughly with a plastic or stainless steel spatula before use. If severe settling is found after a long storage, mix and then jar-roll ink sample overnight before use. It is best to use a polyester screen when printing to minimize contact with reactive metals.

Drying

Allow drying times of 1-2 minutes for well ventilated ovens or conveyor dryers at 120°C. For box oven drying, allow 3-5 minutes at 120°C.

Clean up Solvent

Ethylene glycol diacetate or dipropylene glycol methyl ether work well.

Compatibility

Only print-treated polyester film substrate should be used. DuPont 5874 can also be printed over silver (DuPont 5000 and DuPont 5025) or over carbon (DuPont 7102).

Table 1
Typical Physical Properties

Test	Properties
Density (g/cc)	3.39
Cross Hatch Adhesion (B) [ASTM Norm D3359078]	5
Coverage (cm ² /g)	53.1 @ 1 mil
Coat Weigh (mg/cm ²) [160-mesh screen]	11
Resistivity (mΩ/sq/mil)	70 - 90
Ag Depletion (Anode)	> 40 min
AgCl Depletion (Cathode)	> 40 min

Table 2
Composition Properties

Viscosity (Pa.S) [Brookfield 0.5 RVT, Utility cup & spindle SC4-14/6R, 10 rpm, 25°C]	23 - 35
Solids (150°C)[%]	83.4 - 86.4
Thinner	DuPont 3610
Ag:AgCl ratio	65/35

Table 1 & 2 show anticipated typical physical properties for DuPont 5874 based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

Equipment Consideration

Only print-treated polyester film substrate should be used. DuPont 5874 can also be printed over silver (DuPont 5000, DuPont 5025) or over carbon (DuPont 7102). Care should be taken to minimize contact of silver/silver chloride compositions with metals, especially reactive metals such as aluminum or brass, no contact should occur. Components made of these materials can be protected by taping or covering with an inert material.

Storage and Shelf Life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25°C). Shelf life of material in unopened containers is three months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

Safety and Handling

For Safety and Handling information pertaining to this product, read the Material Safety Data Sheet (MSDS).

Copyright © 2009 DuPont. All rights reserved. The DuPont Oval, DuPont™, The miracles of science™, Green Tape™ and all products or words denoted with ® or ™ are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates ("DuPont").

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF DUPONT.

Caution: Do not use in medical applications involving implantation in the human body or contact with internal body fluids or tissue unless the product is provided by DuPont under a formal written contract consistent with the DuPont Policy Regarding Medical Applications of DuPont Materials H-50103-2 ("Medical Applications Policy") and which expressly acknowledges the contemplated use. For additional information, please request a copy of DuPont Medical Caution Statement H-50102-2 and the DuPont Medical Applications Policy.

The information provided herein is offered for the product user's consideration and examination. While the information is based on data believed to be reliable, DuPont makes no warranties, expressed or implied as to the data's accuracy or reliability and assumes no liability arising out of its use. The data shown are the result of DuPont laboratory experiments and are intended to illustrate potential product performance within a given experimental design under specific, controlled laboratory conditions. While the data provided herein falls within anticipated normal range of product properties based on such experiments, it should not be used to establish specification limits or used alone as the basis of design. It is the product user's responsibility to satisfy itself that the product is suitable for the user's intended use. Because DuPont neither controls nor can anticipate the many different end-uses and end-use and processing conditions under which this information and/or the product described herein may be used, DuPont does not guarantee the usefulness of the information or the suitability of its products in any given application. Users should conduct their own tests to determine the appropriateness of the products for their particular purpose.

The product user must decide what measures are necessary to safely use the product, either alone or in combination with other products, also taking into consideration the conditions of its facilities, processes, operations, and its environmental, health and safety compliance obligations under any applicable laws.

This information may be subject to revision as new knowledge and experience become available. This publication is not to be taken as a license to operate under, or recommendation to infringe any patent.



The miracles of science™

For more information on DuPont 5874 or other DuPont Microcircuit Materials products, please contact your local representative:

Americas

DuPont Microcircuit Materials
14 T.W. Alexander Drive
Research Triangle Park, NC 27709
Tel.: 800-284-3382

Europe

Du Pont (U.K.) Limited
Coldharbour Lane
Bristol BS16 1QD
U.K.
Tel.: 44-117-931-3191

Asia

DuPont Kabushiki Kaisha
Sanno Park Tower, 11-1
Nagata-cho 2-chome
Chiyoda-ku, Tokyo 100-611
Japan
Tel.: 81-3-5521-8650

DuPont Taiwan Ltd
45, Hsing-Pont Road,
Taoyuan, Taiwan 330
Tel.: 886-3-377-3616

DuPont China Holding Co. Ltd
Bldg 11, 399 Keyuan Rd., Zhangji Hi-Tech Park,
Pudong New District, Shanghai 201203, China
Tel.: 86-21-6386-6366 ext.2202

DuPont Korea Inc.
3~5th Floor, Asia tower #726,
Yeoksam-dong, Gangnam-gu
Seoul 135-719, Korea
Tel.: 82-10-6385-5399

E. I. DuPont India Private Limited
7th Floor, Tower C, DLF Cyber Greens,
Sector-25A, DLF City, Phase-III,
Gurgaon 122 002 Haryana, India
Tel.: 91-124-4091818

Du Pont Company (Singapore) Pte Ltd
1 HarbourFront Place, #11-01
HarbourFront Tower One,
Singapore 098633
Tel.: 65-6586-3022

<http://mcm.dupont.com>

MCM5874 (5/2014)